



Compressor Oil Compatibility Guide for Process Gas and Materials

Purpose

The information presented in this bulletin is intended only as a general guide and lists common materials and their levels of compatibility with AMSOIL compressor oils/coolants. Changes in the manufacture, environment and application may cause unpredictable effects in a material's compatibility. Process gases compatibility is listed on the reverse side.

Compatibility Level Definitions

Compatible: There is generally no negative effect on the lubrication performance or the material in question.

Marginal: The effect on the materials/lubricant is dependent on their use and composition, which can vary. An evaluation of the specific material and the specific operating conditions should be done prior to use.

Not recommended: Materials/lubricant which have been found to be adversely affected under most circumstances and should not be considered for use where excessive contact with the subject lubricant and material is involved.

AMSOIL PC Series Compressor Oils

Compatible: Petroleum oils, most synthetic oils, most seals, paints and plastics used in compressors.

Not recommended: As a replacement for systems using polyglycol-based compressor oils such as Sullair Sullube 32[®], Ingersoll-Rand SSR Ultra-coolant[®] or for silicon-based oils such as Sullair Sullube 24 KT[®].

PC Series compressor oils are also not recommended for use with PVC air lines and polycarbonate bowls (unless the bowls are metal-caged).

AMSOIL SIROCCO[®] Synthetic Ester Compressor Oil

Compatible: Petroleum oils, most synthetic oils, as well as seals, paints and plastics as detailed on the following compatibility chart. Compatible with and recommended as a replacement for polyglycol-type compressor oils such as Sullair Sullube 32[®] and Ingersoll-Rand SSR Ultra-coolant[®].

Not recommended: For use with silicon compressor oils such as Sullair Sullube 24 KT[®] or for use with PVC air lines and polycarbonate bowls (unless the bowls are metal-caged).

* Sullair Sullube 32[®] and Sullair Sullube 24 KT[®] are registered trademarks of Sullair Corporation; Ingersoll-Rand SSR Ultra-coolant[®] is a registered trademark of Ingersoll-Rand Company. SIROCCO[®] is a registered trademark of AMSOIL INC. The product code for SIROCCO[®] is SEI.

AMSOIL Compressor Oil Compatibility Chart

Compatible	Marginal	Not Recommended
<p>Paints</p> <p>Epoxy Baked phenolic Oil-resistant alkyd Two-component urethane Moisture-cured urethane</p>	<p>Paints</p> <p>Phenolic Single-component urethane Industrial latex</p>	<p>Paints</p> <p>Acrylic Latex (household) Vinyl (PVC) Varnish Lacquer Polyurethane</p>
<p>Plastics</p> <p>Nylon Fluorocarbon (Teflon®) Polyacetal (Delrin®, Celcon®) Polybutylene terephthalate (PBT) Polypropylene (high density)</p>	<p>Plastics</p> <p>Polyurethane Polyethylene Phenylene oxide (Noryl) Polycarbonate (Lexan) Polysulfone</p>	<p>Plastics</p> <p>Polystyrene Polyvinyl chloride ABS (acrylonitrile/butadiene/styrene) Polycarbonate (bowls)</p>
<p>Rubbers/Seals</p> <p>Fluorocarbon (Viton®) Nitrile rubber (Buna-N, NBR)* Fluorosilicone rubber Polysulfide (Thiokol) Polyester (Hytrel)</p> <p>*High nitrile (>36% acrylonitrile)</p>	<p>Rubbers/Seals</p> <p>Nitrile (Buna-N, NBR)* Polyurethane Ethylene-propylene teropolymer (EPDM) Epichlorohydrin Polyacrylate rubber Silicone rubber</p> <p>*Medium nitrile (30-36% acrylonitrile)</p>	<p>Rubbers/Seals</p> <p>Polychloroprene (Neoprene) Natural rubber Styrene-butadiene rubber (SBR, Buna-S) Butyl rubber Chlorosulfonated polyethylene Nitrile rubber (Buna-N, NBR)*</p> <p>*Low nitrile (<30% acrylonitrile)</p>
<p>Metals</p> <p>Steel and alloys Aluminum and alloys Copper and alloys Tin Nickel Inconel, Monel</p>	<p>Metals</p> <p>Cadmium Zinc Lead</p>	<p>Metals</p>

Process Gases Suitable for Use with SIROCCO®, DC Series and PC Series Oils

Inert or Reducing Gases

Nitrogen, hydrogen, helium, carbon monoxide, carbon dioxide (dry).

Hydrocarbon Gases

Ethylene, ethane, methane, propane, butane, propylene, butylene, natural gas, benzene, butadiene.

Other Gases

Furnace (crack gas), hydrogen sulfide (dry), synthetic gas, sulfur dioxide.

Process Gases Not Recommended

Oxygen, halogen gases, hydrogen chloride, ammonia.

For further information on other gases, contact the AMSOIL Industrial Lubricants Department.

